

PTFE0L - Teflon®

NON-SHRINK, POLYTETRAFLUOROETHYLENE TUBING LIGHT WALL (AWG Spaghetti sized tubing)

Applications

PTFE0L is a light wall non-shrink, flame retardant polytetrafluoroethylene tube. It is designed for a wide range of applications requiring high heat-resistance.

Features

- ★ Continuous operating temperature: -75 °C to +260 °C (-103 °F to +500 °F)
- ★ Highly heat-resistant
- ★ High resistance to chemicals and oils

Standards

- ★ Declared Dimension Life (DDL) 12 years
- ★ Meets V-0 Flammability
- ★ RoHS & REACH Compliant

Specification Values

Property		Test Method	Value	
	Specific Gravity (Max.)	ASTM D792	2.20	
DI : 1	Elongation (Min.)	ASTM D638	200%	
Physical	Tensile Strength (Min.)	ASTM D638	2500 psi	
	Hardness Durometer	ASTM D2240	D-60	
Electrical	Dielectric Strength	ASTM D149	1400 Volts/mil	
	Volume Resistivity (Min.)	ASTM D257	$10^{18}\Omega\cdot cm$	
General	Chemical/Solvent Resistance	-	Excellent	
	Water Absorption (Max.)	ASTM D570	0.01	
	Flammability Rating	UL 94	V-0	

Rev. March 2024





Fax: (469) 568-0808



PTFE0L - Teflon®

NON-SHRINK, POLYTETRAFLUOROETHYLENE TUBING LIGHT WALL (AWG Spaghetti sized tubing)



Product Dimensions

AWG Size	Inside Diameter						
	Internal Diameter in (D)		Internal Diameter mm (D)		Wall Thickness (Nominal) (t)		
	Min	Max	Min	Max	in	mm	
32	.007	.011	.180	.280	.006 ± .002	.152 ± .051	
30	.010	.015	.254	.381	.006 ± .002	.152 ± .051	
28	.013	.018	.330	.480	.006 ± .002	.152 ± .051	
26	.016	.021	.410	.560	.006 ± .002	.152 ± .051	
24	.020	.026	.510	.670	.006 ± .002	.152 ± .051	
23	.023	.029	.584	.740	.006 ± .002	.152 ± .051	
22	.025	.032	.640	.810	.006 ± .002	.152 ± .051	
21	.029	.035	.740	.890	.006 ± .002	.152 ± .051	
20	.032	.040	.813	1.02	.006 ± .002	.152 ± .051	
19	.036	.044	.914	1.12	.006 ± .002	.152 ± .051	
18	.040	.049	1.02	1.25	.006 ± .002	.152 ± .051	
17	.045	.054	1.14	1.37	.006 ± .002	.152 ± .051	
16	.051	.061	1.30	1.55	.006 ± .002	.152 ± .051	
15	.057	.067	1.45	1.70	.006 ± .002	.152 ± .051	
14	.064	.074	1.63	1.88	.008 ± .002	.203 ± .051	
13	.072	.082	1.83	2.08	.008 ± .002	.203 ± .051	
12	.081	.091	2.06	2.31	.008 ± .002	.203 ± .051	
11	.091	.101	2.31	2.57	.008 ± .002	.203 ± .051	
10	.102	.112	2.59	2.85	.008 ± .002	.203 ± .051	
9	.114	.124	2.90	3.15	.008 ± .002	.203 ± .051	
8	.129	.141	3.28	3.58	.008 ± .002	.203 ± .051	
7	.144	.158	3.66	4.01	.008 ± .002	.203 ± .051	
6	.162	.178	4.11	4.52	.010 ± .003	.254 ± .076	
5	.182	.198	4.62	5.03	.010 ± .003	.254 ± .076	
4	.204	.224	5.18	5.69	.010 ± .003	.254 ± .076	
3	.229	.249	5.82	6.33	.010 ± .003	.254 ± .076	
2	.258	.278	6.55	7.06	.010 ± .003	.254 ± .076	
1	.289	.311	7.34	7.90	.010 ± .003	.254 ± .076	
0	.325	.347	8.26	8.81	.012 ± .003	.304 ± .076	

Rev. March 2024





Tel: (469) 568-0800 Fax: (469) 568-0808